

# Cubic Ink Rigid 200 VP

Prototyping material for the maker industry

<b>Tensile Properties (DIN EN ISO 527)</b>	<b>Value<sup>1</sup></b>	<b>Unit</b>
Ultimate Tensile Strength	50	MPa
Tensile Modulus	2500	MPa
Elongation at Break	6	%
HDT B (DIN EN ISO 75)	55	°C
<b>Hardness Properties</b>		
Shore hardness	D80	
<b>Print Appearance/Color</b>		
Available in cyan, magenta, yellow, black, white and grey. More colors on request.		
<b>Availability and Storage</b>		
Available in 1L, 5L and 20L containers.		